



### + APPLICATIONS

SEACORK®DECK is used as a non-slip liner for boat decks. Thanks to its aesthetics and insulating properties, this natural material offers the best qualities required for a super comfortable, marine resistant, secure and longlasting decking option. SEACORK®DECK is available in plates (sheets) and blades (strips).

### + COMPOSITION

SHEET :

Cork Granulate (2 to 4 mm)

Binder : thermoplastic resin



### + SIZES

Dimensions (mm)	Tolerance	Thickness (mm)	Tolerance
1000X500	±8mm	3, 4, 5 & 6	±0,5 mm
2000x500		3, 4, 5,6, 8 & 12	
2000x 47 (73, 103 & 125)		6, 8, 12	

### + ADVANTAGES

- ✓ Very good heat insulator
- ✓ Very good sound insulator
- ✓ Does not rot
- ✓ Naturally anti-slip, even underwater
- ✓ Excellent dimensional stability
- ✓ Light weight
- ✓ Easy maintenance
- ✓ Easy application
- ✓ Easy repair



### + PERFORMANCE

MECHANICAL :

Density	400 kg/m <sup>3</sup>	ISO 7322
Traction	Mini 15 daN/cm <sup>2</sup>	ISO 7322
Compressibility	15 à 20%	ISO 7322
Lenghtening	Mini 10%	ISO 7322
Weight for thick. 8 mm	≈ 3,2 kg/m <sup>2</sup>	ISO 7322
Weight for thick. 4 mm	≈ 1,6 kg/m <sup>2</sup>	ISO 7322



THERMAL :

Specific heat :	> 1500 J/kg.K	
Thermal Conductibility	(λ) 0,05 à 0,06 W/m.K	
Thermal diffusivity	< 1,60.10 <sup>-7</sup> m <sup>2</sup> .s	

### + STORAGE

Good storage condition are required: 20°C (± 3°C) and 60% humidity (± 5%)

### + WARRANTY 5 years

Aegir Cork Goup SAS - 234 avenue de la Gare 40310 Gabarret FRANCE

Tel: +33 5 58 52 32 01 Email: [info@seacork.com](mailto:info@seacork.com)

SAS au capital de 45000€ RCS - Mont de Marsan 75095787000025 TVA 25750957870

FABRICATION, INSTALLATION & DISTRIBUTION AGENT :

Liège Marine SAS, FRANCE  
contact: +33 6 23 03 64 85  
email : [info@liegemarine.com](mailto:info@liegemarine.com)

SIRET: 821 790 144 00017  
APE/NAF: 3315Z  
EU TAX: FR14 821 790 144

