Polishing Antifouling

Antifouling

PRODUCT DESCRIPTION

Polishing Antifouling is an antifouling product effective against fouling organisms; slime, aquatic plants and animals. A Polishing Antifouling suitable for professional and consumer application onto vessels in fresh and salt water. Provides protection for up to one year. Can be applied up to 6 months before launch.

PRODUCT INFORMATION

Colour YPL000-Off White, YPL001-Red, YPL002-Blue, YPL003-Navy, YPL004-Black

Finish Matt

Specific Gravity1.5 averageTypical Shelf Life2 yearsVolume Solids51% average

VOC (as supplied) 427 g/L average

VOC (EU Solvent) 286 g/kg average EU Solvent Emissions Directive (Council Directive 1999/13/EC)

Unit Size 750mL, 2.5L

DRYING/OVERCOATING INFORMATION

	Drying						
	5°C (41°F)	15°C (59°F)	23°C (73°F)	35°C (95°F)			
ch Dry ersion	1 hr 8 hrs	45 mins 6 hrs	30 mins 4 hrs	20 mins 4 hrs			

Note: Max. Immersion Times are as follows: 5-35°C - 6 months

Overcoating Ambient / Substrate Temperature

	5°C (41°F)		15°C (59°F)		23°C (73°F)		35°C (95°F)		
Overcoated By	Min	Max	Min	Max	Min	Max	Min	Max	
Polishing Antifouling	16 hrs	Ext.	10 hrs	Ext.	6 hrs	Ext.	4 hrs	Ext.	_

APPLICATION AND USE

Touc

Preparation PREVIOUSLY ANTIFOULED SURFACE

In Good Condition: All fouling and contamination must be thoroughly removed including the leached layer. Use high pressure fresh water wash (3000 psi/207 bar) and/or scraping and wet sanding with typically 80-120 grade paper. Do not dry sand. If old antifouling is incompatible or unknown, seal with suitable sealer coat.

In Poor Condition: Remove all traces of antifouling.

PRIMING: All preparation for bare substrates is covered on the appropriate primer datasheet.

Bare GRP: Prime using suitable primer for osmosis protection Steel / Iron / Lead / Wood: Prime with anti-corrosive primer.

Hints Mixing Thoroughly stir until product is mixed to a uniform consistency before use.

Thinning Thinning is not recommended. Antifouling performance can be compromised if correct dry film

thickness is not applied.

Airless Spray Pressure 176-220 bar / 2500-3200 psi. Tip size: 517 to 521 Ventilation and Humidity Control Ensure adequate ventilation during use

Other Antifouling should only be wet sanded. Never dry sand or burn-off antifoulings. True colour will

develop after immersion.

Polishing Antifouling

Antifouling

To prevent premature failure, ensure the correct amount of paint is applied using the coverage as a guide. **Some Important Points**

Product and ambient temperature should be minimum 5°C and maximum 35°C.

Substrate temperature should be minimum 1°C above dew point and maximum 35°C.

Suitable for use on GRP, Wood, Steel/Iron and Lead. Not suitable for use over Aluminium/Alloy and Zinc-Compatibility/Substrates

sprayed surfaces.

Can be applied direct over most types of antifoulings, provided they are in sound condition, with the

exception of PTFE antifoulings.

Application Methods Airless Spray (Professional only), Brush, Roller

By Brush / Roller: **Number of Coats**

Apply 2 coats of 50 microns dry for 12 months (Total DFT of 100 microns)

By Spray: (Professional only)

Apply 1 coat of 100 microns dry for 12 months (Total DFT of 100 microns)

In all schemes, apply an extra stripe coat in areas of high wear such as chines, rudders, sterngear

and any leading edges.

Recommended DFT per coat 50 microns dry per coat by brush / roller

100 microns dry per coat by spray

98 microns wet per coat by brush / roller Recommended WFT per coat

196 microns wet per coat by spray

By Brush / Roller: Coverage

(Theoretical) – 10m²/L per coat (Practical) – 9m²/L per coat

By Spray: (Professional only) (Theoretical) - 5m²/L per coat (Practical) - 3m²/L per coat

TRANSPORTATION, STORAGE AND SAFETY INFORMATION

GENERAL INFORMATION Storage

Exposure to air and extremes of temperature should be avoided. For the full shelf life of this product to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/41°F and

35°C/95°F. Keep out of direct sunlight.

TRANSPORTATION

The product should be kept in securely closed containers during transport and storage.

Safety GENERAL

Antifoulings should only be wet sanded. Never dry sand or burn-off old antifoulings.

Read the label safety section for Health and Safety Information, also available on the Safety Datasheet.

DISPOSAL

Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal. Remainders of this product cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.

IMPORTANT NOTES

The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.